
















Classificazione secondo EN 14411 ISO 13006 annesso G gruppo B1A con E ≤0,5 % UGL - Classification in accordance with En 14411 ISO 13006 annex G standards B1A with E ≤ 0,5% UGL
 Classification selon En 14411 ISO 13006 annexe G groupe B1A avec E ≤0,5% UGL - Klassifizierung gemäß EN 14411 ISO 13006 anlage G Gruppe B1A mit E ≤0,5% UGL
 Классификация в соответствии с EN 14411 ISO 13006, приложение G, стандарт B1A, где E ≤0,5% UGL

	CARATTERISTICA TECNICA TECHNICAL CHARACTERISTIC CARACTERISTIQUE TECHNIQUE TECHNISCHE DATEN ТЕХНИЧЕСКАЯ ХАРАКТЕРИСТИКА	NORMA NORMS NORME NORM НОРМА	VALORE * MEDIO "CAESAR" AVERAGE "CAESAR" VALUE * VALEUR * MOYEN "CAESAR" "CAESAR" DURCHSCHNITTSWERT * СРЕДНЕЕ ЗНАЧЕНИЕ "CAESAR" *	VALORE * MEDIO "CAESAR" AVERAGE "CAESAR" VALUE EXTRA 20i OUTDOOR FLOORS
	Dimensione - Size Dimension - Abmessungen - Размер	ISO 10545-2	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Assorbimento d'acqua* - Water absorption* Absorption d'eau* - Wasseraufnahme* - % Поглощения воды*	ISO 10545-3	0,05%	0,05%
	Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* - Упругость*	ISO 10545-4	Conforme - In accordance Conforme - Erfüllt - Соответствует	Non applicable a piastrelle con una forza di rottura ≥ 3000 N Not applicable to tiles with a breaking strength ≥ 3000 N N'est pas applicable aux carreaux avec une charge de rupture ≥ 3000 N Nicht anwendbar bei Fliesen mit einer Bruchlast ≥ 3000 N Не применяется в отношении плиток с прочностью на разрыв ≥ 3000 N
	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Estuero de ruptura	ISO 10545-4	Sps ≥ 7,5 mm S ≥ 1300 N	> 10.000 N
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* Устойчивость к глубокому истиранию*	ISO 10545-6	≤ 145 mm ²	≤ 145 mm ²
	Coefficiente di dilatazione termica lineare - Thermal linear expansion coefficient coefficient - Coefficient de dilatation thermique linéaire - Koeffizient der linearen thermischen - Dehnung - Коэффициент линейного теплового расширения	ISO 10545-8	≈ 6,5 (10 ⁻⁶ °C ⁻¹)	≈ 6,5 (10 ⁻⁶ °C ⁻¹)
	Resistenza agli sbalzi termici - Thermal shock resistance Résistance aux écarts de température - Temperaturwechsel Beständigkeit Устойчивость к тепловому перепаду	ISO 10545-9	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий
	Dilatazione all'umidità - Expansion in humidity Dilatation à l'humidité - Feuchtigkeitsausdehnung Расширение в условиях влажности	ISO 10545-10	≤ 0,1 (mm/m)	≤ 0,1 (mm/m)
	Resistenza al gelo - Frost resistance Résistance au gel - Frostbeständigkeit - Морозоустойчивость	ISO 10545-12	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий
	Resistenza all'attacco chimico - Resistance to chemical attack Résistance à l'attaque chimique - Beständigkeit gegen Chemikalien Устойчивость к химическому воздействию	ISO 10545-13	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий
	Carico statico - Static load Charge statique - Statische Last Carga estática	EN 12825	-	Centro - Centre - Au centre - Mitte - По центру KN>8,0 Centro lato - Side centre - Au centre latéralement Mitte Seite - По центру грани KN>5,5 Diagonale - Diagonal - En diagonale Diagonal - По диагонали KN>8,0
	Classe di carico di rottura Breaking load class - Classe de charge de rupture Bruchlastklasse - Clase de carga de rotura	EN 1339	-	U11 T11
	Resistenza alle macchie - Resistance to stains Résistance aux taches - Fleckenbeständigkeit Устойчивость к образованию пятен	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся
	Resistenza allo scivolamento** - Slip resistance** Résistance au glissement** - Rutschhemmende Eigenschaft** Спротивление скольжению**	DIN 51130-51097	Naturale Matt - Naturel Natur Матовая R9	Strutturato Textured - Structuré Strukturiert Структурная R11 A+B+C
		ASTM C1028	C.O.F. WET ≥ 0,60 C.O.F. DRY ≥ 0,60	≥ 0,70 ≥ 0,70
		▲ BOT 3000	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Spessore nominale - Nominal Thickness Epaisseur nominal - Nominalstärke Номинальная толщина		22,5x180 - 30x120 - 20x120 - 14,7x120 - 10 mm	60x60 - 20 mm

* **Valori medi riferiti agli ultimi due anni di produzione** - Average values referred to the lasto two years of production - Valeurs moyennes des deux dernières années de production
Durchschnittswerte, die sich auf die letzten zwei Produktionsjahre beziehen - Средние значения относительно последних двух лет производства.

** **Valori relativi alla finitura naturale del prodotto ed a test effettuati da laboratori esterni accreditati, disponibili in azienda; ci rendiamo disponibili alla verifica dell'eventuale lotto interessato all'acquisto.**
As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are available upon request at Headoffice, we are willing to check the lot you are interested in purchasing.
Valeurs se référant à la finition naturelle du produit selon des tests effectués par des laboratoires extérieurs accrédités et à la disposition de toute personne intéressée auprès de nos bureaux; nous sommes disponibles pour le contrôle de l'éventuel lot concerné par l'achat.
Werte bezogen auf das natürliche Produktfinish und in anerkannten externen Labors geprüft, im Unternehmen erhältlich; für eventuelle Prüfungen der zu erwerbenden Warenposten stehen wir gern zur Verfügung.
Значения, касающиеся натуральных характеристик изделий и тестов, выполненных внешними авторизованными лабораториями, имеются компании. Мы готовы выполнить проверку партии товара, которую намереваетесь приобрести.

• **Per prodotti chimici di uso domestico e additivi per piscina** - For domestic chemicals and swimming pool additives - Pour produits chimiques à usage domestique et additifs pour piscines
Für chemische Produkte für den Hausgebrauch und Schwimmbadzusätze - Для бытовых химикатов и добавок для бассейнов.

▲ **Valore minimo richiesto ANSI A137.1 - 2012 > 0,42** - Minimum Value Required ANSI A137.1 - 2012 > 0,42 - Valeur Minimum Demandée ANSI A137.1 - 2012 > 0,42 - Erforderlicher Mindestwert ANSI A137.1 - 2012 > 0,42
Минимальное требуемое значение по ANSI A137.1 2012 >0,42